

Application Technical area, building
Manufacturing: Only mechanically and thermic bonding.
Article: Nonwoven Needlefelt
Composition: Chemical Fibers

Specification	Unit	Set point	Method
Thickness	mm	0,70 ± 0,15	Thickness gauge Käfer JD200 p = 1,1 kPa; A = 19,2 cm ²
Weight	g/m ²	110 ± 11	DIN EN 29073 -1 100 cm ² circle stamped out
Tensile strength	N/5cm N/5cm	> 110 MD > 150 CD	DIN EN 29073 – 3 Clamp distance = 200 mm Tensile speed = 200 mm/min Pre load = 1,0 N
Elongation at break	% %	> 60 MD > 60 CD	DIN EN 29073 – 3 see Tensile strength
Form of delivery			
Roll Width	cm	According to the order	---
Diameter cardboard tube	mm	According to the order	---
Roll Length	m	According to the order	---

Data concerning our products and devices as well as concerning our data and procedures are based on an extensive research work and an application technology experience. We obtain these results, with which we do not take over adhesion going beyond the respective single contract, in word and writing after best knowledge, reserve ourselves we however technical changes in the course of the product development. Beyond that our application technology service stands when desired for large consultation as well as for co-operation with the solution manufacturing and application technology problems for order. That does not relieve the user however to examine our data and recommendations before their use responsible for the own use. That applies - particularly for deliveries to foreign markets - also regarding the keeping of patent rights third as well as for applications and procedures, which are not expressly in writing indicated by us. The case of loss our adhesion is limited to indemnifications of same extent, as they plan our general terms of delivery and sales with lack of quality.