

**Application:** In winter time or when coating cold rooms, the cold cement concrete floor must often be reconstructed. Plastifloor® resins can be used up to -22°F in extreme cases. However from 41°F downwards, curing by only adding Plastifloor® hardener powder 50 W is not possible. By adding Plastifloor® Accelerator 101 reactivity will considerably increase and thus fast curing is being ensured.

**Properties:** Accelerator 101 provokes an increased radical formation after it has diluted in the Plastifloor® binder and been mixed with the hardener. Thus with simultaneous increase of the hardener quantity, polymerisation and thus curing of the coating is ameliorated or only enabled first. Adding Plastifloor® Accelerator 101 increases the yellowing of clear polymers (e.g. sealers). Higher concentrations also reduce mechanical strength.

**Characteristics:**

---

Delivery form:	yellowish liquid
Density at 20 °C:	0.0022 lb/cm <sup>3</sup>
Flash point:	+ 181 °F

---

**Safety advice:** Plastifloor® accelerator must be stored strictly separate from the hardener powder and must never be directly mixed with the hardener powder: **risk of deflagration!!**

Blend Accelerator 101 only shortly before processing with the binder!  
Accelerator 101 is toxic, avoid skin contact!  
Imperatively pay attention to the advice in the safety data sheets.

**Bundle size:** 2,2 lb, larger quantities on request

**Processing/  
dosage:**

Mix Plastifloor® accelerator 101 only shortly before processing with the Plastifloor® resin. Hardener powder and fillers are to be added last. Binder and fillers have to be cooled down to substrate or surrounding temperature as pot life and curing times would extremely be shortened otherwise.

Deviating from the indications on the product data sheets, the following dosages have to be observed imperatively. Dosage depends on temperature and resin type.

**Storage instructions:** Store Platifloor® Accelerator 101 in plastic containers, never in metal containers as a chemical reaction with those cannot be excluded.

Furthermore a maximum storage time of 6 months has to be observed.

## Accelerator and hardener addition for PF 112 N, PF 332 N, PF 418 N, PF 800 N

Temperatur [°F]	Accelerator 101 [w/w %]	Hardener 50 W [w/w %]
32	0,5	5
14	1	5
-4	2	5
-22	3	5

Stir in accelerator and hardener powder one after the other very thoroughly!

Do not add Accelerator to any of the sealings as this may cause strong yellowing aspects.

**Attention:** **At temperatures below 32°F the exact dosages of hardener and accelerator have to be tested by the processor before using.** In many cases it is very helpful to put the resin in a warm environment (minimum 5°C) before processing. It is very important to dry the subfloor completely and have an adequate layer thickness.

data concerning our products and tools as well as concerning our data and procedures are based on extensive research work and application-technical experience. We procure these results in word and writing to our best knowledge but do not assume liability going beyond the respective single contract. However we reserve the right to technical alterations in the course of product development. This does not absolve the user from testing our products and procedures on their qualification for his purposes. The same goes for ensuring property rights of thirds as well as for applications and procedures that have not been explicitly given by us in writing.