

# Plastifloor® - 112 N (USA)

Fast-curing 2-component- adhesive primer

for concrete and cement screed

**PLASTI CHEMIE**  
**Produktionsgesellschaft mbH**

---

**Application** Primer 112 N serves as adhesive primer for Plastifloor® coatings, especially on cement-bound substrates.

**Characteristics:** Primer 112 N is a reactive methacrylate resin that also cures fast on low temperatures.

**Characteristic data:**

---

Delivery form	slightly cloudy liquid	
Flowtime	30 - 40 sec	(DIN cup 0,1574 inch)
Curing	10 - 20 min	(68°F with 2% hardener 50W)
Density	DIN51757 ~ 1.00	(68°F) g/cm <sup>3</sup>
Flashpoint	50°F	
Shelf life	In the original container, dark at < 65°F maximum 6 months	

---

**Processing Notes:**

Processing: Primer 112 N must be mixed with hardener 50 W. Hardener quantity must be adjusted to the respective object temperature (see table). At temperatures below + 41°F, accelerator B101 can additionally be added, must be added (~ 0.5 % at 32 °F up to 3 % at - 22 °F) with retention of 6 p.b.v. hardener powder.

After mixing in the hardener powder, spread Plastifloor® 112 N equally and thinly with a roller or rubber squeegee (80-100 ft<sup>2</sup>/gal). Consumption must be adjusted individually. On extremely absorbent substrates, prime twice in order to achieve a thin but closed film that bonds the broadcasting material. We recommend slightly broadcasting the primer with quartz sand (size 15 - 25 mesh). If only thin sealers are to be applied, we recommend using quartz sand in size 20 - 40 mesh. This work step ensures an absolutely solid bond between primer and the following coating.

Suggested formulation:

2.00 gal primer 112 N  
~ 6 oz hardener 50 W (at 68°F ground temperature)

# Plastifloor® - 112 N (USA)

Fast-curing 2-component- adhesive primer

for concrete and cement screed

**PLASTI CHEMIE**  
**Produktionsgesellschaft mbH**

---

## Material

consumption: 80-100 ft<sup>2</sup>/gal per Work step

## Pot life and curing

times depending

on temperature:

Further coating layers with Plastifloor® must only be applied after the previous layers have completely cured.

Temperature [°F]	Hardener [Vol-%] *	Pot life [min]	Curing time [min]
32 - 41	6	~ 11	~ 30
41 - 50	5	~ 8	~ 30
50 - 59	4	~ 8	~ 30
59 - 68	3	~ 7	~ 25
68 - 77	2	~ 6	~ 20
77 - 86	1	~ 6	~ 20

\* Hardener quantity calculated on pure resin (Hardener 50 W)

**Attention:** Hardener quantities below 1 Vol. % may cause polymerisation failures!

## **Storage:**

The handling-regulations for highly flammable materials apply to methacrylate – resins. Plastifloor® resins are to be stored cool, protected against direct sunlight and preferably at temperatures of 59 - 68 °F. During storage paraffin – particles and filler – materials may precipitate. Thus before processing, containers have to be stirred up well. Please mind the advice on our safety data sheets.

Data concerning our products and devices as well as concerning our data and procedures are based on an extensive research work and an application technology experience. We obtain these results, with which we do not take over adhesion going beyond the respective single contract, in word and writing after best knowledge, reserve ourselves we however technical changes in the course of the product development. Beyond that our application technology service stands when desired for large consultation as well as for co-operation with the solution manufacturing and application technology problems for order. That does not relieve the user however to examine our data and recommendations before their use responsible for the own use. That applies - particularly for deliveries to foreign markets - also regarding the keeping of patent rights third as well as for applications and procedures, which are not expressly in writing indicated by us. The case of loss our adhesion is limited to indemnifications of same extent, as they plan our general terms of delivery and sales with lack of quality.

02.03.2021

2 / 2